Application No.: 10/722,177

Case No.: 58962US002

## **Listing of Claims:**

The following Listing of Claims will replace all prior listings of claims in the application. Applicants note that none of the claims are being amended.

- 1. (Original) A coating solution comprising:
  - (a) surface-modified nanoparticles;
  - (b) a first liquid having a vapor pressure, VP1; and
- (c) a second liquid miscible with the first liquid, having a vapor pressure, VP2, that is less than VP1, wherein the nanoparticles are more compatible with the first liquid than with the second liquid.
- 2. (Original) The coating solution of claim 1, wherein the second liquid is curable.
- 3. (Original) The coating solution of claim 2, wherein the second liquid is curable by heat, actinic radiation, electron beam radiation, moisture, or combinations thereof.
- 4. (Original) The coating solution of claim 1, further comprising a crosslinker.
- 5. (Original) The coating solution of claim 1, wherein the second liquid is selected from the group consisting of: acrylates, methacrylates, epoxies, polyesters, polyols, isocyanates, polystyrene, polyacrylates, polymethacrylates, polyurethanes, and combinations thereof.
- 6. (Original) The coating solution of claim 1, wherein the first liquid is selected from the group consisting of: water, organic solvents, inorganic solvents, and combinations thereof.
- 7. (Original) The coating solution of claim 6, wherein the organic solvent is selected from the group consisting of: alcohols, ketones, aromatic hydrocarbons, and combinations thereof.
- 8. (Original) The coating solution of claim 1, wherein the second liquid is selected from the group consisting of: water, organic solvents, inorganic solvents, and combinations thereof.

ЗМ

Case No.: 58962US002

- 9. (Original) The coating solution of claim 8, wherein the second liquid is 1-methoxy-2-propanol acetate.
- 10. (Original) The coating solution of claim 1, further comprising a material selected from the group consisting of dyes, pigments, fillers, electrically conductive particles, thermally conductive particles, fibers, film-forming polymers, catalysts, initiators, and combinations thereof.
- 11. (Original) The coating solution of claim 10, wherein the film-forming polymer is polymethylmethacrylate.
- 12. (Original) The coating solution of claim 1, wherein the second liquid is an acrylate, optionally wherein the acrylate is selected from the group consisting of isooctyl acrylate, 2-ethylhexyl acrylate, 1,6-hexanediol diacrylate, and combinations thereof.
- 13. (Original) A method of enhancing coating uniformity comprising:
  - (a) applying the coating solution of claim 1 to a surface of a substrate;
- (b) removing at least a portion of the first liquid, optionally wherein removing comprises evaporation, and optionally wherein removing at least a portion of the first liquid comprises removing substantially all of the first liquid.
- 14. (Original) The method of claim 13, further comprising:
- (c) removing at least a portion of the second liquid, optionally wherein removing comprises evaporation, and optionally wherein removing at least a portion of the second liquid comprises removing substantially all of the second liquid.
- 15. (Original) The method of claim 13, further comprising curing and/or crosslinking the second liquid.

ЗМ

Case No.: 58962US002

Application No.: 10/722,177

- (Original) A coated substrate made by the method of claim 13. 16.
- (Original) The coated substrate of claim 16, wherein the substrate is selected from the 17. group consisting of: glass, metal, polymer, wood, ceramic, paper, fabric, and combinations thereof.
- (Original) A coated substrate made by the method of claim 14. 18.
- 19. (Original) The coated substrate of claim 18, wherein the substrate is selected from the group consisting of: glass, metal, polymer, wood, ceramic, paper, fabric, and combinations thereof.
- 20. (Original) A coated substrate made by the method of claim 15.
- (Original) The coated substrate of claim 20, wherein the substrate is selected from the 21. group consisting of: glass, metal, polymer, wood, ceramic, paper, fabric, and combinations thereof.